

Solvoya® UA4046-W

Edition 04-2020

Solvoya® UA4046-W is a polyurethane modified long oil alkyd based on soya bean oil or soya oil F.A, available in solids of 60±1% in white spirit.

Mode of application: Air physical dry

PERFORMANCE & APPLICATIONS

- Light color with good yellowing resistance
- Excellent abrasion, chemicals & water resistance
- Fast drying time properties
- Excellent compatibility with majority of medium & long alkyds
- Good outdoor durability
- Recommended for varnishes for parquet and furnitures
- Recommended for interior pigmented decorative enamels
- Used for wood varnishes & Yacht varnishes

SUPPLY SPECIFICATIONS

• Delivery form	60.0 ± 1%
• Dilution form	60.0 ± 1%
• Gardner viscosity at 25°C	Approx. Z3 at 60%
• Brookfield approx. viscosity at 25°C	Approx. 4,600 CP at 60%
• Gardner Color Scale DIN EN ISO 6271-1	2.0 max.
• Acid value mg KOH/gm solid	4.0 max.

TYPICAL COMPOSITION

• Phthalic anhydride content	28%
• Type of oil	Soya bean oil or soya bean F.A
• Oil Content	60%
• Type of Polyol	Penta
• Type of Solvent(s)	White spirit
• Type of isocyanate	Aromatic

SPECIFIC PROPERTIES

• Aliphatic hydrocarbon	Soluble
• Aromatic hydrocarbon	Soluble
• Chlorinated hydrocarbon	Soluble
• Alcohols	Insoluble
• Ketones	Soluble

STORAGE

Solvoya® UA4046-W is stable at temperatures from 5 °C up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

STABILITY

Solvoya® UA4046-W is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.